For a Free Quote: Web: EnergyPal.com/solar Call: 1-800-990-3725 Email: contact@energypal.com

EnergyPa


Solar Panel Guide Specification Data Sheet

Jiangsu Guoyang Photoelectric Technology Co., Ltd. 6P-70-80 6P-75

Also available on the web at EnergyPal.com/jiangsu-guoyang-photoelectric-technology-co-ltd-solar-panels/6p-75

POLYCRYSTALLINE SILICON MODULE









Add:CuiB ei Industrial Park , Henglin T own, Wujin District, Changzhou City, Jiangsu Province, China. Tel: +86-519-85260699 Fax:+86-519-85260299 Email:Inf o@ gsunp.com Web Side: www.gsunp.com

6P-70 6P-75 6P-80 POLYCRYSTALLINE SILICON MODULE

Products Characteristics

	Widely using of the most popular and mature type of modules for off-grid system.		
	Leading manufacturing technology in PV industry, strictly controlling the quality of raw materials and the process of producing		
EL	100% EL inspection, ensures modules are defects free.		
939	Cells binned by current to improve module performance		
	Anti reflective glass. Not only to increase the light absorption, but also to make the module has the function of self-cleaning in water environment, effectively reducing the power loss caused by dust.		
	Outstanding performance in low-light irradiance environments.		
5400 Pa	Excellent mechanical load resistance:Certified to withstand high wind loads(2400pa) and snow loads(5400pa).		
	High salt and ammonia resistance		
0~+5	Positive power tolerance:0-+5w		

Warranty

- 10 years product warranty
- 10-years 90% of Min. rated output power,and 25-years 80% of Min. rated output power warranty

Comprehensive Certificates


- ISO Certificate
- SGS-TUV Certificate
- CQC Certificate
- IEC61215、IEC61730 Certificate
- CE Certificate

Specifications subject to technology and test conditions, GSUN Power reserves the right of final interpretation


6P-70 6P-75 6P-80

GEUN POWER WWW.GSUNP.COM

Engineering Drawings (Front Side)



▼ Engineering Drawings (Back Side)



Add:CuiB ei Industrial Park , Henglin T own, Wujin District, Changzhou City, Jiangsu Province, China. Tel: +86-519-85260699 Fax:+86-519-85260299 Email:Inf o@ gsunp.com Web Side: www.gsunp.com

Raw materials and Mechanical Parameters

	6P-70	6P-75	6P-80	
Type of Cells(mm)	р	poly156×78/156×39		
NO. of Cells and Connections		4×9=36/4×18=72		
Dimensi ons(mm)(L*W*H)	780×670×30			
Weight(kg)	5.9			
Glass	3.2mmTempered Glass			
Encapsulation	EVA			
Backsheet	Multilayer Composite			
Aluminium-Frame	Silvery/Black Anodized aluminiu m alloy			
Junction-Box	IP65/IP67			
Cable	NA, but customized is acceptable			
Connector	NA, but MC4 and	NA, but MC4 and MC4 Compatible are acceptable		
Package Configuration		6pcs/ctn		

Performance Parameters

	6P-70	6P-75	6P-80
Maximum System Voltage		700V	
Operating Temperature		-45~+80°C	
Maximum Series Fuse		10A	
Maximum Static Load,Front Side (e.x. S	now,Wind)	5400PA	
Maximum Static Load, Back Side(e.x. Win	d)	2400PA	
Application Grade		Class A	

Electrical Parameters (Standard Test Condition)

	6P-70	6P-75	6P-80
Rated Maximum Power(Mp)	70W	75W	80W
Power Tolerance		0-+5W	
Cell Efficiency	16.2%	17.2%	18.3%
Open Circuit Volt age(Voc)	21.5V	22.3V	22.6V
Maximum Power Volt age (Vmp)	17.6V	18.2V	18.5V
Short Circuit Current(lsc)	4.22A	4.37A	4.58A
Maximum Power Current(Imp)	3.98A	4.12A	4.32A
Temperature Coefficient of Isc		+0.06%	
Temperature Coefficient of Voc		-0.33%	
Temperature Coefficient of Pmp		-0.45%	
Standard Test Condition	Irradiance:1000W/M2,Cell Temperature:25°C,Spectrum AM:1.5		

The Electrical Parameters of the module are the average theory figure under the standard test condition, each one exists difference. Can not be treated as the basis of module delivery.