For a Free Quote:

Web: EnergyPal.com/solar

Call: 1-800-990-3725

Email: contact@energypal.com



Solar Panel Guide Specification Data Sheet

EverExceed Industrial Co., Ltd ESM340S-156 ESM340S-156





ESM340S-156

MONOCRYSTALLINE SOLAR MODULE



High module conversion efficiency through superior, manufacturing technology



Easy installation and handling for various applications



Entire module certified to withstand high wind loads (2400 Pa) and snow loads (5400 Pa)



ISO9001,OHSAS18001, ISO14001













An EverExceed high-power residential solar module isan aesthetic addition to most roofs

ENGINEERING EXCELLENCE

The perfect combination of high performance and design

ADVANCEDAESTHETICS

Has an elegant appearance that blends beautifully with your home roof line

DURABLE

Provides long life and enhanced cell performance

HIGH PERFORMANCE

Uses advanced surface texturing to improve efficiency



EverExceed PV modules offer BTS-leading performance for a variety of applications

Power your application

When you choose EverExceed ,you get more well-engineered products, you also get our proven reliability, outstanding customer service and the assurance of our 25-year limited warranty



340 Watt

Electrical Characteristics	
Type of Cell	Monocrystalline silicon
Cell Size(mm)	156x156mm
Module Efficiency	17.52%
Cell Configuration	72(6x12)
Size of module (mm)	1956x992x35mm
Weight per piece (Kg)	21Kg
Maximum power (Wp)	340W
Maximum power voltage (V)	38.1V
Maximum power current (A)	8.92A
Open circuit voltage (V)	46.1V
Short circuit current (A)	9.38A
Tolerance of Pmax	0~+5W

Standard Operating Conditions		
Maximum system voltage (V)	1000V	
Temperature coefficients of Isc (%)	0.05%/°C	
Temperature coefficients of Voc (%)	-0.31%/°C	
Temperature coefficients of Pm (%)	-0.41%/°C	
NOCT(°C)	45°C±2°C	
Temperature range	-40°C to +85°C	
Surface maximum load capacity	60m/s (200kg/sq.m)	
Series fuse rating	15A	

Other Characteristics	
Junction box type	lp67 rated
Connectors and cables type	4mm²
Length of cables (mm)	900mm
Frame (material, corners, etc.)	Anodized aluminum alloy
Glass	High transmissivity low-iron 3.2 mm toughened glass
FF (%)	≥ 78.59%

QUALIFICATIONS IEC 61215 IEC 61730 RoHS C EMC





